

THERMAL INSULATING ROLLS
COUPLED WITH BITUMINOUS
MEMBRANES

Roll XPS



ROLL XPS is an insulating system in rolls, made up of strips of insulating material, combined and coupled by heat on a bituminous waterproofing membrane. On demand is available a special selvedge for sealing the overlaps, 8 cm wide on polyester versions and 5 cm on fiberglass versions, composed of a strip self-adhesive protected by siliconized polyethylene. The sealing of the side overlaps always occurs by self-adhesion while the head overlaps or however on the slate, they must be sealed with the help of bituminous mastic PRATIKO MASTIC or, when it is possible, they can be welded with hot air. This special selvedge allows a fast and safe application (without using flame). ROLL XPS are recommended for the insulation and waterproofing of covers in general, with the great convenience of using a single product; in fact, they offer the high thermal insulation capacity of extruded polystyrene and the waterproofness of a bituminous membrane. ROLL XPS are made of extruded polystyrene (XPS), closed cell, self-extinguishing RF class E, in compliance with the requirements of European Directive 89/106/ECC and are produced considering and applying the EN 13164 product standards with the CE marking.

Fields of use

ROLL XPS fit any type of cover: flat, sloped and curved. They are quick to apply and once installed, thanks to the overlapping flange, the cover is already waterproofed. After installing the ROLL XPS, a second waterproofing membrane or the definitive roof covering can be applied. ROLL XPS is a thermal insulating system that can be adapted to multiple forms of roofing, but also for the insulation and protection of retaining walls.

Installation

ROLL XPS should be anchored according to the nature and the slope of the application surface and local weather conditions (windy, cold weather etc.) using adequate mechanical fasteners, with suitable bonding systems or with appropriate bossed membranes. ROLL XPS offers high resistance to mechanical stress together with high thermal and acoustic insulation; the system's bituminous component is exclusively to protect the insulating element. Laying of the next gripping layer must be carried out in total adhesion and on top of the underlying membrane.

MEMBRANE TECHNICAL CHARACTERISTICS	M.U.	REFERENCE NORM	P	P	PA	PA	PA	V	V	TOLERANCE
REINFORCEMENT TYPE			Single strand polyester					Fibreglass		
UPPER FACE FINISH			PE film		Mineral*			PE film		
LOWER FACE FINISH			PE film							
THICKNESS	mm	EN 1849-1	3	4				2	3	±5%
MASS	kg/m ²	EN 1849-1			3,5	4,0	4,5			±10%
COLD FLEXIBILITY	°C	EN 1109				-10				
FLOW RESISTANCE	°C	EN 1110				120				
FLOW RESISTANCE AFTER AGEING	°C	EN 1296		110		110				-10°C
SHEAR RESISTANCE L / T	N / 5 cm	EN 12317-1	300/200							±20%
TENSILE STRENGTH L / T	N / 5 cm	EN 12311-1			400/300			300/200		±20%
ELONGATION AT BREAK L / T	%	EN 12311-1			35/35			2/2		±15 / ±2
TEAR RESISTANCE L / T	N	EN 12310-1			130/130			70/70		±30%
DIMENSIONAL STABILITY	%	EN 1107-1			-0,3			NPD		
LOSS OF MINERAL SLATE	%	EN 12039				30				
STATIC PUNCTURE RESISTANCE	kg	EN 12730	10							
DYNAMIC PUNCTURE RESISTANCE	mm	EN 12691	700							
FIRE RESISTANCE		EN 13501-5				F ROOF				
REACTION TO FIRE		EN 13501-1				F				
TENSILE STRENGTH AFTER AGEING L / T	N / 5 cm	EN 1296				NPD				±20%
IMPERMEABILITY AFTER ARTIFICIAL AGEING	kPa	EN 1296			60					
WATERTIGHTNESS	kPa	EN 1928			60					

* Mineral self-protected products may undergo color tone variations due to the time and length of storage. Exposure to atmospheric conditions, after application, will tend to uniform the color after a few months. The change in color tone cannot therefore be contested and / or complained of as it is a natural phenomenon that the slate manufacturer himself cannot guarantee.

NPD = No Performance Declared in accordance with the EU Construction Products Directive.

XPS technical specifications

(In compliance with current EN 13164 standards)

**THERMAL INSULATING ROLLS
COUPLED WITH BITUMINOUS
MEMBRANES**

CHARACTERISTICS	M.U.	XPS	ROLL LENGTH (M)
AVAILABLE THICKNESSES	mm	30	9
	mm	40	7
	mm	50	5
	mm	60	4



CHARACTERISTICS	SYMBOL M.U.					NORM
		30	40	50	60	
Declared thermal conductivity	λ_D (10°C W/mk)	0,034		0,035		UNI EN 13164
Declared heat resistance $R_D = d/\lambda_D$	R_D (m²K/W)	0,88	1,17	1,42	1,71	UNI EN 13164
Dimensional stability at 70°C with 90% RH	DS (TH) (%)	≤ 5				EN 1604
Deformation under load 40 kPa 70°C	DLT (2) (%)	≤ 5				EN 1605
Operating limit temperature	°C	+75				UNI EN 14706
Compressive strength at 10% deformation	σ_{10} (kPa)	≥ 200		≥ 250		UNI EN 826
Tensile strength	σ_{mt} (kPa)	> 400				EN 1607
Water absorption in the long term by total immersion (28 days)	WL (T) (%)	≤ 1				UNI EN 12087
Water vapour transmission by diffusion	μ	80	70	65		UNI EN 12086
Reaction to fire	Euroclass	E				UNI EN 11925-2 UNI EN 13501-1
Coefficient of linear thermal expansion	mm/mK	0,07				UNI EN ISO 1923
Specific heat	C_p (J/kgK)	1450				UNI EN ISO 10456
Closed cells	CV %	> 95				UNI EN ISO 4590
Water absorption in the long term by diffusion (28 days)	Vol. %	≤ 5		≤ 3		EN 12088

DIMENSIONAL TOLERANCE

THICKNESS	mm	< 50 from 50 to 60	-2; +2 -2; +3	UNI EN 823	T1
-----------	----	-----------------------	------------------	------------	----

The data reported in this table refer to a bare, uncoupled panel.

We reserves the rights to change or modify the nominal values without prior notice or advice. The information contained in this data sheet are based on our experience. We cannot take any responsibility for a possible incorrect use of the products. The customer has to choose under their own responsibility a product fit for the intended use.

THERMAK
info@thermak.it
www.thermak.it

MATCO S.r.l.
Via Quadrelli, 69
37055 Ronco all'Adige (VR)
Tel. +39.045.6608111

